



8565 W 44th Ave. Suite
106, Hialeah, FL 33018

ASPHALT TYPE IV

Cinducoat 230 built-up roofing asphalt is formulated from the world's finest crude oil sources. Type IV asphalt for special steep, supplied in 100 lb cartons, meet or exceed ASTM D312 specification.



REQUIREMENTS	TYPE III	TYPE IV	TEST METHODS
SOFTENING POINT (°F)	108-205	210-225	ASTM D36
FLASH POINT (°F)	550	550	ASTM D92
PENETRATION UNITS @32 (°F) @77 (°F) @155 (°F)	6 15 35 90	6 12 25 75	ASTM D5
DUCTIBILITY @77 (°F), cm	2.5	1.5	ASTM D113
SOLUBILITY IN TRICHLOROETHYLENE 99%	99	99	ASTM D2042
*exceeds ASTM D312			